



# **SWFR**

## Single Wall, Heat Shrink Tubing Highly flame-retardant, UL VW-1 rated, Zerohal tubing

#### PRODUCT DESCRIPTION

SWFR tubing from TE Connectivity (TE) is a cost effective, highly flame-retardant, 2:1 shrink ratio tubing made irradiated, cross-linked polyolefin. It insulates and mechanically protects components, electrical connections, and terminations. SWFR is offered in two very flexible types. X2 is a thin wall tubing, and X4 is a very thin wall tubing. The thicker wall of the X2 offers better protection, while the space-saving thinner wall of the X4 permits denser packing of protected components and a faster shrink time to better protect against thermal damage of temperature-sensitive components. Both types are halogen free, permitting their use in enclosed spaces where toxic gasses from burning materials containing halogens is undesirable.

### **KEY FEATURES**

- Highly flame-retardant with UL VW-1 and CSA OFT flammability rating
- Environmentally friendly formula is essentially free of halogens, permitting use in enclosed areas where emission of toxic gasses from burning materials containing halogens is undesirable.

#### **APPLICATIONS**

- Household appliances
- Automotive
- Commercial electronics & communications
- Consumer products
- Industrial equipment

## STANDARDS AND SPECIFICATIONS

- Customer drawings: SWFR X2 and SWFR X4
- UL 224 VW-1, CSA OFT
- UL file E35586
- CSA file LR31929

#### ELECTRICAL, MECHANICAL, & MATERIALS

- Provides excellent electrical insulation
- Provides mechanical protection from abrasion
- Highly flexible X2 thin wall & X4 very thin wall types
- Non-halogenated irradiated polyolefin
- RoHS & REACH compliant

#### TEMPERATURE RATING

- Minimum shrink temperature 70°C [158°F]
- Full recovery temperature 90°C [194°F]
- Operating temperature -30°C to 125°C [22°F to 257°F]

#### ORDERING INFORMATION

- Color: Black (-0)
- Packaging: (-SP) spool, varying lengths (consult TE for details) & (-FSP) flat on spool (only for sizes 8mm & larger)
- Ordering description: Specify product type, size, color & packaging. For example, X2-2/1-0-SP
- Standard product is unmarked, but marking on product is available on a special order basis

#### **DIMENSIONS**



| Product Type           | Size | Minimum<br>Expanded I.D. (D) | Maximum<br>Recovered I.D. (d) | Total Recovered<br>Wall Thickness (W) |
|------------------------|------|------------------------------|-------------------------------|---------------------------------------|
|                        | 1.0  | 1.3                          | 0.5                           | 0.44                                  |
|                        | 1.5  | 1.9                          | 0.75                          | 0.44                                  |
|                        | 2.0  | 2.4                          | 1.0                           | 0.44                                  |
|                        | 2.5  | 2.9                          | 1.25                          | 0.44                                  |
|                        | 3.0  | 3.4                          | 1.5                           | 0.44                                  |
|                        | 3.5  | 3.8                          | 1.75                          | 0.46                                  |
|                        | 4.0  | 4.3                          | 2.0                           | 0.46                                  |
|                        | 5.0  | 5.3                          | 2.5                           | 0.56                                  |
| X2 (Thin Wall)         | 6.0  | 6.3                          | 3.0                           | 0.56                                  |
|                        | 7.0  | 7.3                          | 3.5                           | 0.56                                  |
|                        | 8.0  | 8.3                          | 4.0                           | 0.56                                  |
|                        | 9.0  | 9.3                          | 4.5                           | 0.56                                  |
|                        | 10.0 | 10.1                         | 5.0                           | 0.56                                  |
|                        | 12.0 | 12.4                         | 6.0                           | 0.56                                  |
|                        | 18.0 | 18.6                         | 9.0                           | 0.77                                  |
|                        | 25.0 | 26.4                         | 12.5                          | 0.77                                  |
|                        | 30.0 | 31.6                         | 15.0                          | 0.89                                  |
|                        | 0.8  | 0.95                         | 0.4                           | 0.25                                  |
|                        | 1.0  | 1.15                         | 0.5                           | 0.25                                  |
|                        | 1.5  | 1.65                         | 0.75                          | 0.25                                  |
|                        | 2.0  | 2.05                         | 1.0                           | 0.26                                  |
|                        | 2.5  | 2.55                         | 1.25                          | 0.28                                  |
|                        | 3.0  | 3.05                         | 1.5                           | 0.28                                  |
| X4 (Very Thin<br>Wall) | 3.5  | 3.55                         | 1.75                          | 0.28                                  |
|                        | 4.0  | 4.15                         | 2.0                           | 0.28                                  |
|                        | 6.0  | 6.1                          | 3.0                           | 0.33                                  |
|                        | 9.0  | 9.1                          | 4.5                           | 0.33                                  |
|                        | 13.0 | 13.2                         | 6.5                           | 0.41                                  |
|                        | 18.0 | 18.6                         | 9.0                           | 0.46                                  |
|                        | 25.0 | 25.4                         | 12.5                          | 0.46                                  |

## PRODUCT DESCRIPTION & ORDERING INFORMATION

| Product<br>Type   | Material<br>Description | Material<br>Number |  |
|-------------------|-------------------------|--------------------|--|
| .,,,,,            | X2-1.0-0-SP             | EJ1477-000         |  |
|                   | X2-1.5-0-SP             | EJ1478-000         |  |
|                   | X2-2.0-0-SP             | EJ1479-000         |  |
|                   | X2-2.5-0-SP             | EJ1480-000         |  |
|                   | X2-3.0-0-SP             | EJ1481-000         |  |
|                   | X2-3.5-0-SP             | EJ1482-000         |  |
|                   | X2-4.0-0-SP             | EJ1483-000         |  |
| \(\alpha \)       | X2-5.0-0-SP             | EJ1484-000         |  |
| X2 (Thin<br>Wall) | X2-6.0-0-SP             | EJ1485-000         |  |
| vvany             | X2-7.0-0-SP             | EJ1486-000         |  |
|                   | X2-8.0-0-FSP            | EJ1488-000         |  |
|                   | X2-9.0-0-FSP            | EJ1489-000         |  |
|                   | X2-10.0-0-FSP           | EJ1490-000         |  |
|                   | X2-12.0-0-FSP           | EJ1492-000         |  |
|                   | X2-18.0-0-FSP           | EJ1497-000         |  |
|                   | X2-25.0-0-FSP           | EJ1500-000         |  |
|                   | X2-30.0-0-FSP           | EJ1502-000         |  |

| Product<br>Type        | Material<br>Description | Material<br>Number |  |
|------------------------|-------------------------|--------------------|--|
|                        | X4-0.8-0-SP             | EJ1505-000         |  |
|                        | X4-1.0-0-SP             | EJ1506-000         |  |
|                        | X4-1.5-0-SP             | EJ1507-000         |  |
|                        | X4-2.0-0-SP             | EJ1508-000         |  |
|                        | X4-2.5-0-SP             | EJ1509-000         |  |
|                        | X4-3.0-0-SP             | EJ1510-000         |  |
| X4 (Very<br>Thin Wall) | X4-3.5-0-SP             | EJ1511-000         |  |
|                        | X4-4.0-0-SP             | EJ1512-000         |  |
|                        | X4-6.0-0-SP             | EJ1514-000         |  |
|                        | X4-9.0-0-FSP            | EJ1517-000         |  |
|                        | X4-13.0-0-FSP           | EJ2608-000         |  |
|                        | X4-18.0-0-FSP           | EJ2612-000         |  |
|                        | X4-25.0-0-FSP           | EJ2616-000         |  |



### X2 THIN WALL PROPERTY REQUIREMENTS

| Property                      | Unit               | Requirement                                                             | Test Method  |  |
|-------------------------------|--------------------|-------------------------------------------------------------------------|--------------|--|
| Physical                      |                    |                                                                         |              |  |
| Dimensions                    | mm                 | As shown in DIMENSIONS table                                            | ASTM D 2671  |  |
| Longitudinal change           |                    |                                                                         |              |  |
| ASTM D 2671                   | percent            | +1, -5                                                                  | ASTM D 2671  |  |
| UL 224                        | percent            | +3, -3                                                                  | UL 224       |  |
| Eccentricity (recovered)      | percent            | 30 maximum                                                              | ASTM D 2671  |  |
| Tensile strength              | MPa ( <i>psi</i> ) | 10.3 (1500) minimum                                                     | ASTM D 2671  |  |
| Ultimate elongation           | percent            | 200 minimum                                                             | ASTM D 2671  |  |
| Secant modulus (as supplied)  | MPa ( <i>psi</i> ) | 172 (2.5 x 10 <sup>4</sup> ) maximum                                    | ASTM D 2671  |  |
| Low-temperature flexibility   |                    |                                                                         |              |  |
| (1 hour at -30°C/-22°F)       |                    | No cracking                                                             | UL 224       |  |
| Heat shock                    |                    | No ovaclina                                                             | UL 224       |  |
| (4 hours at 250°C/482°F)      |                    | No cracking                                                             | OL 224       |  |
| Heat aging                    |                    |                                                                         | 111.004      |  |
| (7 days at 158°C/316°F)       |                    |                                                                         | UL 224       |  |
| Followed by tests for:        |                    |                                                                         |              |  |
| Tensile strength              | MPa (psi)          | 70% minimum of unaged specimens                                         | UL 224       |  |
| Ultimate elongation           | percent            | 100 minimum                                                             | UL 224       |  |
| Flexibility                   |                    | No cracking                                                             | ASTM D 2671  |  |
| Dielectric withstand at 2500V | seconds            | 60 minimum                                                              | ASTM D 2671  |  |
| Dielectric breakdown          | volts              | 50% minimum of unaged specimens                                         | UL 224       |  |
| Dielectric strength           | kV/mm (volts/mil)  | 19.7 (500) minimum                                                      | ASTM D 2671  |  |
| Restricted shrinkage          |                    | Pass                                                                    | UL 224       |  |
| Electrical                    |                    |                                                                         |              |  |
| Dielectric withstand at 2500V | seconds            | 60 minimum                                                              | ASTM D 2671  |  |
| Dielectric strength           | kV/mm (volts/mil)  | 19.7 (500) minimum                                                      | ASTM D 2671  |  |
| Volume resistivity            | ohm-cm             | 10 <sup>14</sup> minimum                                                | ASTM D 2671  |  |
| Chemical                      |                    |                                                                         |              |  |
| Corrosive effect              |                    | No corrosion                                                            | ASTM D 2671  |  |
| (7 days at 158°C/316°F)       |                    | INO COITOSIOTI                                                          | A3111 D 20/1 |  |
| Copper stability              |                    | No brittleness, glazing, cracking,                                      |              |  |
| (7 days at 158°C/316°F)       |                    | or severe discoloration of tubing.  No pitting or blackening of copper. | ASTM D 2671  |  |
| Followed by tests for:        |                    |                                                                         |              |  |
| Ultimate elongation           | percent            | 100 minimum                                                             | ASTM 2671    |  |
| Flammability                  |                    | Pass                                                                    | UL 224, VW-1 |  |

## X4 VERY THIN WALL PROPERTY REQUIREMENTS

| Property                      | Unit               | Requirement                                                             | <b>Test Method</b> |
|-------------------------------|--------------------|-------------------------------------------------------------------------|--------------------|
| Physical                      |                    |                                                                         |                    |
| Dimensions                    | mm                 | As shown in DIMENSIONS table                                            | ASTM D 2671        |
| Longitudinal change           |                    |                                                                         |                    |
| ASTM D 2671                   | percent            | +1, -15                                                                 | ASTM D 2671        |
| UL 224                        | percent            | +3, -3                                                                  | UL 224             |
| Eccentricity (recovered)      | percent            | 30 maximum                                                              | ASTM D 2671        |
| Tensile strength              | MPa ( <i>psi</i> ) | 10.3 (1500) minimum                                                     | ASTM D 2671        |
| Ultimate elongation           | percent            | 200 minimum                                                             | ASTM D 2671        |
| Secant modulus (as supplied)  | MPa ( <i>psi</i> ) | 103 (1.5 x 10 <sup>4</sup> ) maximum                                    | ASTM D 2671        |
| Low-temperature flexibility   |                    | No sussides                                                             | 111 224            |
| (1 hour at -30°C/-22°F)       |                    | No cracking                                                             | UL 224             |
| Heat shock                    |                    | No exacting                                                             | 111 224            |
| (4 hours at 250°C/482°F)      |                    | No cracking                                                             | UL 224             |
| Heat aging                    |                    |                                                                         | 111.004            |
| (7 days at 158°C/316°F)       |                    |                                                                         | UL 224             |
| Followed by tests for:        |                    |                                                                         |                    |
| Tensile strength              | MPa (psi)          | 70% minimum of unaged specimens                                         | UL 224             |
| Ultimate elongation           | percent            | 100 minimum                                                             | UL 224             |
| Flexibility                   |                    | No cracking                                                             | ASTM D 2671        |
| Dielectric withstand at 2500V | seconds            | 60 minimum                                                              | ASTM D 2671        |
| Dielectric breakdown          | volts              | 50% minimum of unaged specimens                                         | UL 224             |
| Dielectric strength           | kV/mm (volts/mil)  | 19.7 (500) minimum                                                      | ASTM D 2671        |
| Restricted shrinkage          |                    | Pass                                                                    | UL 224             |
| Electrical                    |                    |                                                                         |                    |
| Dielectric withstand at 2500V | seconds            | 60 minimum                                                              | ASTM D 2671        |
| Dielectric strength           | kV/mm (volts/mil)  | 19.7 (500) minimum                                                      | ASTM D 2671        |
| Volume resistivity            | ohm-cm             | 10 <sup>14</sup> minimum                                                | ASTM D 2671        |
| Chemical                      |                    |                                                                         |                    |
| Corrosive effect              |                    | No correction                                                           | ACTM D 2671        |
| (7 days at 158°C/316°F)       |                    | No corrosion                                                            | ASTM D 2671        |
| Copper stability              |                    | No brittleness, glazing, cracking,                                      |                    |
| (7 days at 158°C/316°F)       |                    | or severe discoloration of tubing.  No pitting or blackening of copper. | ASTM D 2671        |
| Followed by tests for:        |                    |                                                                         |                    |
| Ultimate elongation           | percent            | 100 minimum                                                             | ASTM 2671          |
| Flammability                  |                    | Pass                                                                    | UL 224, VW-1       |

#### FOR MORE INFORMATION

Visit www.te.com and enter search term "SWFR," or visit www.te.com/SWFRtubing.

## TE TECHNICAL SUPPORT CENTER

USA: +1 (800) 522-6752 +1 (905) 475-6222 Canada: Mexico: +52 (0) 55-1106-0800 Latin/S. America +54 (0) 11-4733-2200 Germany: +49 (0) 6251-133-1999 UK: +44 (0) 800-267666 +33 (0) 1-3420-8686 France: Netherlands: +31 (0) 73-6246-999 China: +86 (0) 400-820-6015

#### te.com

TE Connectivity, TE Connectivity (logo), Zerohal, and Every Connection Counts are trademarks. All other logos, products and/or company names referred to herein might be trademarks of their respective owners.

The information given herein, including drawings, illustrations and schematics which are intended for illustration purposes only, is believed to be reliable. However, TE Connectivity makes no warranties as to its accuracy or completeness and disclaims any liability in connection with its use. TE Connectivity's obligations shall only be as set forth in TE Connectivity's Standard Terms and Conditions of Sale for this product and in no case will TE Connectivity be liable for any incidental, indirect or consequential damages arising out of the sale, resale, use or misuse of the product. Users of TE Connectivity products should make their own evaluation to determine the suitability of each such product for the specific application.

© 2016 TE Connectivity Ltd. family of companies All Rights Reserved.

1-1773894-4 10/16 Original



# **Mouser Electronics**

**Authorized Distributor** 

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

## TE Connectivity: