

RNF-100 tubing is a high-quality, heat-shrinkable product for a wide variety of uses. It has become the industry standard for insulation, strain relief, wire bundling, and color-coding in both commercial and military applications. RNF-100 tubing meets the requirements of AMS-DTL-23053/5, Class 1 (colors) and Class 2 (clear).

## **RNF-100**



Flexible, flame-retardant, high performance, polyolefin heat-shrinkable tubing

It is also UL-recognized and CSA-certified at 125°C, 600 V.

Made from flame-retardant polyolefin, RNF-100 tubing has excellent physical, chemical, and electrical properties that meet industrial and military requirements for a highly reliable, general-purpose tubing. It sets itself apart in that it offers a higher level of performance at elevated temperature, including mechanical abrasion and fluid resistance, than many heat-shrinkable polyolefin tubings available in the marketplace today.

Only a few sizes of RNF-100 tubing are required to cover many substrate diameters.

### Temperature rating

Minimum shrink temperature:	121°C
Continuous operating temperature:	–55°C to 135°C

Specifications*			<b>.R</b> .	<b>SP</b> •
Туре	Raychem	Military	UL	CSA
RNF-100 Type 1 (colors)	RT-350 Type 1	AMS-DTL-23053/5, Cl. 1	E35586	LR31929
RNF-100 Type 2 (clear)	RT-350 Type 2	AMS-DTL-23053/5, Cl. 2		

\*When ordering, always specify latest issue.

#### Dimensions (millimeters/inches)



	Inside diameter			Wall thickness			Inside diameter			Wall thickness			
	D (mi	n.)	d (m	ax.)	W		-	D (mir	า.)	d (ma	ах.)	W	
	Expar	nded	Rec	overed	Recovered			Expar	nded	Reco	vered	Recovered	
Size	ize as supplied after		heating	ng after heating**		Size as supplied	pplied	after heating		after heating**			
3/64	1.2	0.046	0.6	0.023	$0.40 \pm 0.08$	0.016 ± 0.003	3/4	19.1	0.750	9.5	0.375	0.77 ± 0.08	0.030 ± 0.003
1/16	1.6	0.063	0.8	0.031	$0.43 \pm 0.08$	0.017 ± 0.003	1	25.4	1.000	12.7	0.500	0.89 ± 0.12	0.035 ± 0.005
3/32	2.4	0.093	1.2	0.046	$0.51 \pm 0.08$	0.020 ± 0.003	1 1/4	31.7	1.250	15.9	0.625	1.02 ± 0.15	0.040 ± 0.006
1/8	3.2	0.125	1.6	0.062	$0.51 \pm 0.08$	0.020 ± 0.003	1 1/2	38.1	1.500	19.1	0.750	$1.02 \pm 0.15$	0.040 ± 0.006
3/16	4.7	0.187	2.4	0.093	$0.51 \pm 0.08$	0.020 ± 0.003	2	50.8	2.000	25.4	1.000	1.14 ± 0.16	$0.045 \pm 0.007$
1/4	6.4	0.250	3.2	0.125	$0.64 \pm 0.08$	0.025 ± 0.003	3	76.2	3.000	38.1	1.500	1.27 ± 0.20	0.050 ± 0.008
3/8	9.5	0.375	4.8	0.187	$0.64 \pm 0.08$	0.025 ± 0.003	4	101.6	4.000	50.8	2.000	1.40 ± 0.23	0.055 ± 0.009
1/2	12.7	0.500	6.4	0.250	0.64 ± 0.08	0.025 ± 0.003	5	127.0	5.000	63.5	2.500	1.53 ± 0.23	0.060 ± 0.009

Ordering information

Colors	blors Standard Black (all sizes); clear, white, red, blue, green, and yellow (3/64" through 3")				
	Nonstandard	Clear, white, red, blue, and yellow (4" and 5"); brown, orange, violet, and gray (all sizes)			
Size selection	Always order the largest size that will shrink snugly over the component being covered.				
Standard packaging	On spools or in 4 foot lengths				
Ordering description	Specify product name, size, and color; for example, RNF-100-1/4-BK (BK=Black).				

#### Specification values

	Droporty	Unit	Requirement		Mothod of toot
Discolaria	Property	Unit	Type 1 (colors)	Type 2 (clear)	Method of test
Physical	Dimensions	mm (inches)	See Reverse	See Reverse	ASTM D 2671
	Longitudinal change	percent	+0, -5	+0, -5	ASTM D 2671
	Tensile strength	psi <i>(Mpa)</i>	1500 <i>(10.3)</i> minimum	1500 <i>(10.3)</i> minimum	ASTM D 2671
	Ultimate elongation	percent	200 minimum	200 minimum	ASTM D 2671
	Secant modulus (as supplied)	psi <i>(Mpa</i> )	2.5 X 10 <sup>4</sup> (172) maximum	2.5 X 10 <sup>4</sup> <i>(172)</i> maximum	ASTM D 2671
	Specific gravity		1.35 maximum	1.0 maximum	ASTM D 2671
	Low temperature flexibility (4 hours at -55°C/-67°F)		No cracking	No cracking	AMS-DTL-2305
	Heat shock		No dripping,	No dripping,	AMS-DTL-2305
	(4 hours at 250°C/482°F)		flowing, or cracking	flowing, or cracking	
	Heat resistance (336 hours at 175°C/347°F)				ASTM D 2671
	Followed by test for:				
	Ultimate Elongation	percent	150 minimum	150 minimum	ASTM D 2671
	Color		MIL-STD-104		MIL-STD-104
	Color stability (48 hours at 175°C/ <i>347°F</i> )		MIL-STD-104		ASTM D 2671
Electrical	Dielectric strength	volts/mil <i>(volts/mm)</i>	500 <i>(19,680)</i> minimum	500 <i>(19,680</i> ) minimum	ASTM D 2671
	Volume resistivity	ohm-cm	10 <sup>14</sup> minimum	10 <sup>16</sup> minimum	ASTM D 2671
Chemical	Copper mirror corrosion (16 hours at 175°C/347°F)		No removal of copper	No removal of copper	ASTM D 2671 Procedure A
	Copper contact corrosion (168 hours at 160°C/ <i>320°F</i> )		No pitting or blackening of copper	No pitting or blackening of copper	ASTM D 2671 Procedure B
	Copper stability (16 hours at 160°C/ <i>320°F</i> )		No brittleness, glazing, cracking, or severe discoloration of tubing	No brittleness, glazing, cracking, or severe discoloration of tubing	ASTM D 2671 Procedure B
	Followed by test for:				
	Ultimate Elongation	percent	200 minimum	200 minimum	ASTM D 2671
	Flammability		Self-extinguishing within 1 minute, 25% maximum flag burn		ASTM D 2671 Procedure B
	Fungus resistance		Rating of 1 or less	Rating of 1 or less	ASTM G 21
	Water absorption (24 hours at 23°C/73°F)	percent	0.5 maximum	0.2 maximum	ASTM D 2671
	Fluid resistance (24 hours at 23°C/73°F) in: JP-8 fuel (MIL-T-5624) Skydrol 500 Hydraulic fluid (MIL-H-5606) Aviation gasoline100/300 (MIL-G-5572) Water				ASTM D 2671
	Followed by tests for:			400 (15 7(0)	
	Dielectric strength	volts/mil (volts/mm)	400 <i>(15,760)</i> minimum	400 <i>(15,760)</i> minimum	ASTM D 2671
	Tensile strength	psi <i>(Mpa</i> )	1000 <i>(6.9)</i> minimum	1000 <i>(6.9)</i> minimum	ASTM D 2671

Raychem is a trademark of Tyco Electronics Corporation.

#### Users should independently evaluate the suitability of the product for their application.

Tyco Electronics Corporation			
300 Constitution Drive	Faraday Road	3816 Noborito, Tama-ku	Asia Pacific Headquarters
Menlo Park, CA 94025-1164	Dorcan, Swindon, SN3 5HH	Kawasaki, Kanagawa 214-8533	26 Ang Mo Kio, Industrial Park 2
USA	United Kingdom	Japan	Singapore 569507
Tel: (800) 926-2425 (US & Canada)	Tel: +44 1793 528171	Tel: +81 44 900 5102	Tel: +65 4866 151
Tel: +1 (650) 361-3860 (All other countries)			

All information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics Corporation makes no warranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. Tyco Electronics Corporation's only obligations are those in the Standard Terms and Conditions of Sale for these products and in no case will Tyco Electronics Corporation be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use, or misuse of the product. Tyco Electronics Corporation's Specifications are subject to change without notice. In addition, Tyco Electronics Corporation reserves the right to make changes in materials or processing without notification to the Buyer which do not affect compliance with any applicable specification.

# **Mouser Electronics**

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

TE Connectivity: 5052904010