

## **LOCTITE ABLESTIK G 909**

August 2016

#### PRODUCT DESCRIPTION

LOCTITE ABLESTIK G 909 provides the following product characteristics:

Technology	Ероху
Appearance	gray
Cure	Heat cure
Product Benefits	One component
	High strength
	Non-sag
	Thixotropic
	<ul> <li>Excellent peel strength</li> </ul>
	<ul> <li>High tensile shear strength over a</li> </ul>
	broad temperature range
Application	Assembly
Surfaces	Copper, Aluminum, Fiberglass reinforced
	plastics and Oily steel
Operating Temperature	-40 to 150 °C

LOCTITE ABLESTIK G 909 is designed for very high strength structural bonding especially for dissimilar substrates that will be exposed to a wide range of operating temperatures.

#### TYPICAL PROPERTIES OF UNCURED MATERIAL

S	Specific Gravity	1.15
F	Press Flow, seconds	65
5	Sag Resistance, mm	12.7
5	Shelf Life @ 0 to 4°C (from date of manufacture), months	4.5
F	Flash Point - See SDS	

## TYPICAL CURING PERFORMANCE

### **Cure Schedule**

90 minutes @ 100°C or 30 minutes @ 120°C or 20 minutes @ 150°C

For optimum performance, follow the initial cure with a post cure of 2 to 4 hour at the highest expected use temperature.

Cure schedules are "the time at cure temperature to achieve full product cure". The times does not include the time required to ramp-up to cure temperature.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

#### TYPICAL PROPERTIES OF CURED MATERIAL

## **Physical Properties**

Hardness, Shore D:	
@ 25°C	78
@ 120°C	35

## TYPICAL PERFORMANCE OF CURED MATERIAL

#### Miscellaneous

Tensile Lap Shear Strength:

. onene zap enear enengan	
Aluminium @ 25°C	N/mm <sup>2</sup> 40 (psi) (5,800)
Aluminum @ 100°C	N/mm <sup>2</sup> 20.3 (psi) (2,950)
Steel @ 25°C	N/mm <sup>2</sup> 32.4 (psi) (4,700)

### Peel Strength - Hysol

"T" Peel Strength, ISO 11339:			
Aluminum	N/mm	5.25	
	(lb/in)	(30)	

#### GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

#### Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

## **DIRECTIONS FOR USE**

- 1. Complete cleaning of the substrates should be performed to remove contamination such as oxide layers, dust, moisture, salt and oils which can cause poor adhesion or corrosion in a bonded part.
- 2. Apply adhesive to all surfaces to be bonded and join together.
- 3. In most applications only contact pressure is required.

## Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

## Optimal Storage: 4°C. Storage greater than or below 4°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.



#### Conversions

(°C x 1.8) + 32 = °F kV/mm x 25.4 = V/mil mm / 25.4 = inches N x 0.225 = lb N/mm x 5.71 = lb/in psi x 145 = N/mm<sup>2</sup> MPa = N/mm<sup>2</sup> N·m x 8.851 = lb·in N·m x 0.738 = lb·ft N·mm x 0.142 = oz·in mPa·s = cP

#### Disclaimer

#### Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

## In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

# In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

#### Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. 

® denotes a trademark registered in the U.S. Patent and Trademark Office.

### Reference 1

## **Mouser Electronics**

**Authorized Distributor** 

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

## Loctite:

1188755 1188756 1188757 2892425